

IT040 S3 SRC



DESCRIPTION	NORMA EN ISO 20345:2011	RESULT	REQUIREMENT
UPPER: Printed leather	5.4.3 Tear strength 5.4.6 Water vapor permeability Coefficient	207 N 1,2 mg/cm ² h 18,8 mg/cm ²	≥120 N ≥ 0,8 mg/cm ² h ≥ 15,0 mg/cm ²
VAMP LINING: breathable, abrasion resistance	5.5.1 Tear strength 5.5.2 Abrasion resistance(Wet) Abrasion resistance(Dry) 5.5.3 Water vapour permeability Coefficient	45 N No fori No fori 4,7mg/cm ² h 40,5 mg/cm ²	≥ 15 N 25.600 cicli 12.800 cicli ≥ 2,0 mg/cm ² ≥20,0 mg/cm ²
QUARTER LINING: Breathable, abrasion resistant	5.5.1 Tear strength 5.5.2 Abrasion resistance(Wet) Abrasion resistance(Dry) 5.5.3 Water vapour permeability Coefficient	25 N No fori No fori 11,3 mg/cm ² h 90,6 mg/cm ²	≥ 15 N 25.600 cicli 12.800 cicli ≥ 2,0 mg/cm ² ≥20,0 mg/cm ²
SAFETY TOE CAP: Non-metallic composite safety toe	5.3.2.3 Impact resistance 5.3.2.4 Compression resistance	14,0 mm 14,0 mm	≥ 14 mm ≥ 14 mm
PIERCE-RESISTANCE: Textile pierce proof footbed	5.7.1. Thickness 5.7.3 Water absorption	3,5 mm 72 mg/cm ²	≥ 2,0 mm ≥70,0 mg/cm ²
FOOTBED: Removable, cushioned, antistatic insole	5.7.4.2 Abrasion resistance(Wet) Abrasion resistance(Dry)	No fori No fori	25.600 cicli 12.800 cicli
OUTSOLE: PU 2D, antislip sole SRC	5.8.2 Tear strength 5.8.3 Abrasion resistance 5.8.4 Flexing resistance 5.8.5 Hydrolysi 6.4.5 Oils resistance 5.11 Pressed ceramic tile floor on detergent resistance Flat slip Heel slip Stainless steel plate on glycerine resistance Flat slip Heel slip	10,4 kN/m 50 mm ³ 1,5 mm 2,5 mm 1% 0,32 0,28 0,18 0,14	≥ 8 kN/m ≤ 150 mm ³ ≤ 4,0 mm ≤ 6,0 mm ≤ 12% ≥ 0,32 ≥ 0,28 ≥ 0,18 ≥ 0,13

MISURE : 35-48

EXENA S.r.l.

Via Breda, 7/A – Zona Ind.le A 62012 – CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519

C.F. e P. IVA: 01336080435 – Reg.Imprese MC n.01336080435 – REA MC144207

www.exena.it – info@exena.it – pec: amministrazione@pec.exena.it